



Material & Engineering Laboratory-Taipei

TEST REPORT

REPORT NO.:HV-2004-3-0225-1

PAGE: 1 OF 1

DATE: APRIL 19, 2004

JiangXi Hongtai Industry Group Co., Ltd.
No.116 Gaoxin 6 Road High-Tech Development
Dist Nanchang Jiangxi China

The following merchandise was submitted and identified by the vendor as:

Type of Product : ALUTILE Aluminum Composite Panel
Manufacturer/Vendor : JiangXi Hongtai Industry Group Co., Ltd.
Country of Origin : China

We have tested the submitted sample(s) as requested and the following results were obtained :

Test Results :

Test Items	Test Methods	Test Results
Density(g/cm ³)	ASTM D792	1.34
Shear Strength(MPa)	ASTM D732	28.2
Heat Deflection Temperature(°C)(264 psi)	ASTM D648	>110
Stripping Strength(lbf/per inch of width)	ASTM D903	69
Flexural Strength(MPa)	ASTM D790	114

REMARK : 1.Heat Deflection Temperature test: The depth of testing sample was set up with standard of specimen depth(4.2mm)
2. HV-2004-3-0225 was withdrawn and replaced by this report.

Date of Testing : March 25, 2004~April 16, 2004

The value of required specifications are for reference only.
Conformity judgement is the Applicant's final verdict.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf. Attention is drawn to the limitations of liability, indemnification, and Jurisdictional issues defined therein. The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. 此報告是遵循本公司訂定之通用服務條款所製作發放。請注意此條款列印於背面。本報告之義務，免責，管轄權皆明確規範之。此報告結果除非另有說明僅對檢驗之樣品負責。本報告未經本公司書面許可，不可部份複製。

